

## Exhibit 12



Hi-Grade Materials Co.  
Ready Mix Concrete – Rock & Sand  
17671 Bear Valley Road, Hesperia California 92345  
Phone: (760) 244-9325 ~ Fax: (760) 244-1819

To: Hi-Grade Materials Co.  
Attention: Lori Clifton

17 November 2015

Project: Hi-Grade Materials Co. - Littlerock Quarry  
6500 East Avenue T  
Littlerock, California 93543

Re: Littlerock Pit-Run Material


On 16 November 2015, samples were taken from the "pit" portion of Littlerock quarry and returned to the laboratory to determine basic cleanness results of unprocessed materials and compare them to minimum requirements for various agency standards. The results are as follows:

- ASTM C117-13: Standard Test Method for Materials Finer than No. 200 Sieve in Mineral Aggregates by Washing
  - Result:
    - 8.6%
  - Limitations:
    - ASTM C33-13: Standard Specification for Concrete Aggregates
      - 0-3%
    - Standard Specifications for Public Works Construction (2015 Edition)
      - 0-5%
    - California Department of Transportation 2015 Standard Specifications
      - 0-8%
- California Test 217 (Rev. 2011): Method of Test for Sand Equivalent
  - Result:
    - 49
  - Limitations:
    - California Department of Transportation 2015 Standard Specifications
      - 75 (minimum)
    - Standard Specifications for Public Works Construction (2015 Edition)
      - 75 (minimum)
- California Test 227(Rev. 2012): Method of Test for Evaluating Cleanness of Coarse Aggregate
  - Result:
    - 68
  - Limitations:
    - California Department of Transportation 2015 Standard Specifications
      - 75 (minimum)
    - Standard Specifications for Public Works Construction (2015 Edition)
      - 75 (minimum)

**Please Note:** In regards to the two California Test Methods (217 & 227): 75 is the specified minimum, however standard industry practice targets results of 80 & 90 respectively.

Please refer to the attached document: Laboratory Test Results – Concrete Conformance Aggregate Testing reported by Earth Systems indicating the results we need to achieve per market requirements. Thank you for your time. If you should have any questions, please do not hesitate to contact me at your earliest convenience.

Respectfully,

  
Stefan Reder  
Quality Assurance Manager  
(760) 552-2393  
[sreder@robarenterprises.com](mailto:sreder@robarenterprises.com)